



UNIVERSITÀ DI PARMA

ARCHIVIO DELLA RICERCA

University of Parma Research Repository

An in vitro strategy to assess mitigation of hazardous properties of engineered metal nanoparticles

This is the peer reviewed version of the following article:

Original

An in vitro strategy to assess mitigation of hazardous properties of engineered metal nanoparticles / Bianchi, Massimiliano G.; Allegri, Manfredi; Ferretti, Raffaele; Bussolati, Ovidio; Rotoli, Bianca Maria; Costa, Anna Luisa; Blosi, Magda; Delpivo, Camilla; Bergamaschi, Enrico. - STAMPA. - (2013), pp. 132-132.

Availability:

This version is available at: 11381/2785715 since: 2015-02-20T13:42:43Z

Publisher:

QNano Network

Published

DOI:

Terms of use:

openAccess

Anyone can freely access the full text of works made available as "Open Access". Works made available

Publisher copyright

note finali coverpage

(Article begins on next page)

06 May 2023



Research Infrastructure

QualityNano

Abstract Book

2nd QNano Integrating Conference

“Quality in nanosafety assessment – driving best practice and innovation”

27th February – 1st March 2013,

IMG Conference Centre, Prague, Czech Republic



3.16. An *in vitro* strategy to assess mitigation of hazardous properties of engineered metal nanoparticles

Massimiliano G. Bianchi¹, Manfredi Allegri², Raffaele Ferretti², Ovidio Bussolati², Bianca Maria Rotoli², Anna Luisa Costa³, Magda Blosi³, Camilla Delpivo³, Enrico Bergamaschi¹

¹Dept. of Clinical and Experimental Medicine and ²Dept. of Biomed. Biotech. and Translational Sciences (SBIiT) University of Parma (Italy); ³ISTEC CNR, Faenza (RA), Italy
Email: massimiliano.bianchi@unipr.it

The huge progress in the nanotechnology field has requested the production of increasingly advanced engineered nanoparticles (NPs). In particular, metal-based advanced NPs are widely used in several industrial applications. However, their potential effects on human health during occupational exposure are still incompletely characterized thus far and possible strategies to decrease their hazardous properties are not yet clearly defined. In this project we are developing an *in vitro* approach to test the cytotoxic effects of metal-based NPs, as derived from production lines or modified through coating with organic or inorganic moieties. We have used two cell models widely employed in toxicological studies, the human alveolar cell line A549 and the murine macrophage cell line RAW264.7, to avoid possible limitations due to cell specific effects. Moreover, in order to evaluate the effectiveness of mitigation approaches for NPs endowed with little acute cytotoxicity, additional endpoints, alternative to viability, have also been assessed. Colloidal suspensions of Ag, TiO₂ and ZrO₂ NPs were tested as provided by industries or modified with SiO₂ NPs or citrate used as coating remediation agents. Heterocoagulation of opposite charged phases was applied in order to promote the coating of pristine surfaces by modifying agents. Heterocoagulated sols were obtained by ball milling sols of positive charged Ag, TiO₂ and ZrO₂ NPs with negative charged SiO₂ NPs or citrate ions. Modified samples, obtained by spray-drying and re-dispersing in water the corresponding sols, were also obtained in order to compare reactivity. Original and modified NPs were added to culture media starting from water colloidal suspensions. Viability was determined with the resazurin method in a range of doses from 2.5 to 80 nfg/cm² (0.3125 to 20 µg/cm² for Ag NPs) of monolayer surface at three experimental times (24, 48 and 72h). The expression of the inducible form of nitric oxide synthase (*Nos2*), an indicator of macrophage activation and, hence, of pro-inflammatory activity, was assessed with RT-PCR as an end-point alternative to viability.

Among the NPs tested, only Ag NP caused a significant loss of viability, with an IC₅₀ of about 0.8 µg/cm² for Raw264.7 cells and 2.4 µg/cm² for A549 cells at the 24h-experimental time. In a preliminary experiment, SiO₂ NPs were demonstrated to have no significant effect on cell viability. The comparison between original and SiO₂-coated Ag NPs, performed in the same experiment, suggested a coating-independent mitigation effect of bioreactivity exerted by the spray drying procedure. However, once corrected for the actual Ag content of the spray-dried powder, no significant difference was found in the IC₅₀ values, indicating that neither silica coating nor spray drying mitigate cytotoxicity. The effects on viability of original TiO₂ and ZrO₂ NPs were assessed using P25 Aeroxide TiO₂ NPs as a reference material. These materials did not affect significantly cell viability at any time point tested, so that it was not possible to estimate IC₅₀ values for either cell line. However, titania produced a clear-cut induction of *Nos2* expression in Raw264.7 cells, thus indicating their potential pro-inflammatory activity. Citrate coating did not produce any significant attenuation of the biological effect. In summary, these preliminary results showed no mitigating effect of the surface modifications tested on the biological effects of the engineered NPs investigated. However, the exploitation of this *in vitro* experimental strategy can be useful for the preliminary assessment of the mitigation potential of surface modifications of both low-toxic and high-toxic engineered NPs.

Supported by EU Grant NMP4-SL-2012-280716 (Sanowork Project)